



Standard Specification paragraphs:

Bona SuperSport 2K

The undernoted paragraphs are designed to provide a starting point for the specification of Bona finishes for timber flooring. Information in **blue** should be selected as a choice depending upon the timber species to be coated or to obtain different wear / appearance values. Contractors should consult the product data and SDS information *in addition* to these paragraphs. Detailed instructions regarding overcoating new prefinished and existing surfaces can be found in the **SuperSport Overcoating Information** datasheet.

Preparation

Overcoating

The surface to be coated must be dry and free from oil, wax and other contamination. Clean the surface prior to preparation using Bona Deep Clean and a scrubber / drier machine. Sand the surface as required to ensure that a good physical key is obtained and that on existing floors scratches, etc. are removed.

A trial application must be undertaken before the application proceeds to check the adhesion of Bona SuperSport 2K Finish to the substrate. Detailed instructions regarding trial application can be found in the **SuperSport Overcoating Information** datasheet.

Application

1 / 2 coats of **Bona SuperSport 2K Finish**, applied using a Bona Roller or applicator bar. A coverage rate of 8 – 10 m² / litre should be observed.

Drying time – approx. 3 hours per coat at 20° C / 60% RH

Inter-coat preparation

Ensure that the coating has thoroughly dried before sanding. The **Bona Scrad** system, sanding disc / screen or abrasive grade should be used for the sanding; 150 grit or finer. The floor should be thoroughly cleaned to remove sanding dust, etc. prior to further applications of finish being made.

When applications of finish are made within 24 hours of the previous application no inter-coat sanding is required. It is recommended that the finish is lightly abraded prior to the final application with all specifications.

All coating operations should be made with consideration being given to the prevailing weather conditions and site conditions in accordance with the product label and accepted good practice.

Bona[®]

Phone 1300 882 806