



BONA SuperSport HD

Bona SuperSport HD is a premium 2-component hardwearing finish high-build polyurethane finish specifically developed for timber flooring in sports halls. It complies with the European standard for indoor sports surfaces (EN 14904:2006) and provides a safe surface for optimal performance. The Bona SuperSport system is approved by the international basketball association (FIBA) for the highest level of international competitions.

- EN 14904:2006 (European standard for indoor sports surfaces) compliant
- Certified by FIBA for the highest level of competition
- Outstanding resistance to wear and scuff marks
- Easy to maintain
- Suitable for overcoating prefinished floors
- Classified EC1R for very low emissions

Technical data

| | |
|---------------------|---|
| Type of finish: | 2-component water-based 100% polyurethane finish |
| Solids content: | ~32% |
| VOC: | <60 g / litre (incl. hardener) |
| Sheen (at 60°): | Gloss ~85%, Matt ~20% |
| Mixing ratio: | 0.41 Lt Hardener to 4.59 Lt SuperSport HD (8% by vol.) |
| Pot life: | 3 hours at 20° C (shorter if warmer) |
| Drying time, until: | - Ready for recoating: 3 hours* - Ready for sanding: 12 hours* - Ready for play: 3 days* *Under normal climate conditions 20° C / 60% R.H. with reasonable ventilation |
| Application tools: | Bona Applicator Bar or Bona Roller |
| Application rate: | 8 - 10 m ² / Lt |
| Safety | Finish: Unclassified Hardener: Classified (see Safety Data Sheet) |
| Cleaning: | Wipe tools free from residual material. Clean with a minimum of water. Remove dried material with acetone. |
| Shelf life: | 1 year from date of production in unopened original container |
| Storage/transport: | The temperature must not fall below +5° C or exceed +25° C during storage and transport. |
| Disposal: | Wastes and emptied containers should be handled in accordance with local regulations. |
| Pack size | 5 litres (incl. Hardener) |
| Certifications: | EN 14904:2006 GREENGUARD EMICODE; class EC1R |

Preparation

Ensure the floor is acclimatized to its end-use environment, well sanded, dry and free from sanding dust, oil, wax and other contamination.

Optimal application conditions are between 18 - 25° C and 30 – 60 % relative air humidity. High temperatures and low humidity will shorten the drying time whilst low temperatures and high humidity will lengthen the drying time.

Minimum temperature for use is 13°C.

Bona®

Phone 1300 882 806

Bona SuperSport HD can be used for overcoating factory pre-finished and previously finished floors. Floors treated with wax, polish or similar cannot be overcoated. Suitable surfaces must be prepared before coating. An adhesion test must be carried out before proceeding to coat the floor. Detailed overcoating instructions can be found at www.bona.com.au

Treatment schedule

| Untreated wood | Pre-finished / previously finished floors |
|---------------------------------------|--|
| 1 x SuperSport Primer | |
| 1 x SuperSport HD | Cleaning to remove contamination |
| Light sanding grit 150 | Light sanding for adhesion and to remove scratches |
| 1 / 2 Pure Colour (for zones / areas) | 1 / 2 Pure Colour (for zones / areas) |
| 1 x SuperSport Line Paint | 1 x SuperSport Line Paint |
| 1 / 2 x SuperSport HD | 1 / 2 x SuperSport HD |

NB Bona Pure Colour should not be applied directly to bare wood but must only be applied to wood sealed with a finish application, site or factory applied.

Important notes:

- It is not recommended to apply more than two full coats per day due to an increased risk of excessive wood swelling.
- Plasticizers from rubber-based adhesives on some line marking tape can soften and damage polyurethane finishes. Tapes should have a "low tack" and should be in place for as short a time as possible.

Application

1. Determine how much material is required. Shake the bottle thoroughly before decanting any finish.
2. Add SuperSport Hardener (8%) to the finish and immediately shake the mixture thoroughly, for 1 minute. Use the scales on the product bottles. The finish / hardener mixture should be used directly, or at least within 3 hours.
3. Apply the finish using a Bona Applicator Bar or a Bona Roller. Apply with a smooth flowing action avoiding accumulations of finish. Always maintain a "wet edge" to avoid overlaps.
4. Allow to dry properly before applying further coats of finish or paint. Anticipate slightly longer drying time for each coat that is applied. Ensure good ventilation at all times during the drying process.

If necessary, make an intermediate sanding using the Bona abrasives grit P150 (or finer) or a suitable sanding screen. Clean well before applying a final coat of finish. **Note:** If the previous layer of lacquer has been allowed more than 24 hours drying time then an intermediate sanding is always required. For paint, the limit is 12 hours.

The floor will take light foot traffic approximately 8 hours after the final application. The floor may be played on after 24 hours but remains susceptible to scuffing or marring until completely cured. Approx. 90% hardness is reached after 24 hours and full hardness after 3 days. Do not cover the surface until it is fully cured. Dry clean only, to remove dust, and avoid wet cleaning of the floor during the first week.

Bona[®]

Phone 1300 882 806

Maintenance

Clean the floor with Bona SuperSport Cleaner (frequent use) and Bona SuperSport Deep Clean (for occasional, intensive cleaning if the surface has become slippery). The appearance and condition of the floor should be assessed regularly as part of an ongoing maintenance plan. The floor should be overcoated periodically with additional coats of Bona SuperSport HD to maintain a safe, slip resistant, high performance surface and to prevent the floor from having to be sanded back to bare wood.

Detailed floor care instructions are available at www.bona.com.au

Please note that whilst Bona finishes are designed to provide a sealed surface that is resistant to wear, scuffing and spillage, etc. no surface applied finish system can prevent physical damage to the timber or 'harden' the floor. Indentations in the wood and scratches may be caused by equipment, dropped items, retractable seating, etc. and steps should be taken to reduce the possibility of this occurring.

Bona finishes are non-yellowing and do not change colour due to the effects of UV light. However, Bona finishes cannot prevent the wood itself changing colour due to tannin bleed, the movement of natural oils or the effects of UV light.

Important notes

The information provided is prepared to the best of our current knowledge and makes no claim to be complete. The User is responsible for establishing that the product and recommendations herein are fit for the designated purpose, wood type and present situation before use. Bona can only guarantee the delivered product. A professional and thereby successful application of the product is beyond our control. If in doubt make a preliminary test. The User is required to read and understand all information contained on package labels and safety data sheets before using this product

The Bona logo consists of the word "Bona" in a bold, blue, sans-serif font, followed by a registered trademark symbol (®).

Phone 1300 882 806