

TWO COMPONENT, WATERBORNE COATING

## Powerful performance at top speed









Bona Traffic HD, the high-performance finish for high traffic areas, now delivers superior protection in less time than ever before, outperforming any other finish in terms of speed and durability. Experience unparalleled wear resistance and minimised downtime. Floor owners are now able to get back on the floor just 12 hours after application.

Bona Traffic HD is a powerful solution for commercial areas such as galleries, museums, airports, shopping centres, etc. whilst also being suitable for domestic floors, giving long-lasting protection and preserving the beauty of the floor for its entire lifetime.

- Ultimate speed and durability
- Superior protection for commercial and public areas
- Allows full traffic after 12 hours
- EMICODE EC1 certified for very low indoor emissions





# TWO COMPONENT, WATERBORNE COATING

## Powerful performance at top speed

# **TECHNICAL DATA**

**Product type:** 2-component waterborne polyurethane topcoat

**Solids content:** approx. 32%

Sheen (at 60°): Silk matt 40%, Matt 20%, Extra Matt 11% (on glass)

Mixing ratio: 1 part hardener to 1 litre Traffic HD

0.41 L hardener to 4,54 L Traffic HD (≈8 vol%)

Pot life: max. 4 hours at 20° C (shorter if warmer)

**Dilution:** If required, dilute with 4% Bona Retarder for a longer open time.

**Drying time, until:** Recoating: 2 - 3 hours\*

Light use: 6 hours\*
Possible to cover: 3 days\*

\*Under normal climate conditions, 20° C / 60% R.H.

Application tools: Bona Microfleece Roller or Bona Swivel Head Bar Applicator.

**Application rate:** 8 - 10 m<sup>2</sup>/L per coat **Safety** Coating: Unclassified

Hardener: Classified. (see Safety Data Sheet).

Cleaning: Wipe tools free from residual material. Clean with a minimum of water. Remove dried

material with acetone.

Shelf life: Coating: 1 year from date of production in unopened original container

Hardener: 18 months from the date of production in unopened original container

Storage/transport: The temperature must not fall below +5° C or exceed +30° C during storage and

transport.

**Disposal:** Waste and emptied containers should be handled in accordance with local regulations.

Pack size 4.95 L incl. hardener (0,41 L)

Certificates: EMICODE EC1 Very low emission

GREENGUARD Gold

EN 14904:2006; approved friction for sports floors

EN 13501-1; Reaction to fire

Qualifies for LEED and BREEAM points.

Additional detailed information is noted in the appropriate Safety Data Sheet.

## **PREPARATION**

Ensure the floor is acclimatised to its end-use environment, well sanded, dry, and free from sanding dust, oil, wax and other contamination.

Allow lacquer and hardener to reach room temperature, insert filter and shake the container thoroughly before use. Optimal conditions for use are between 18 - 25° C and 30-60% relative humidity. High temperatures and low humidity shorten drying times, low temperatures and high humidity lengthen drying times.

Minimum temperature for use is 13° C.





TWO COMPONENT, WATERBORNE COATING

## Powerful performance at top speed

### TREATMENT SCHEDULE

#### Standard application:

1 x Bona Primer <sup>1</sup>

2 x Bona Traffic HD <sup>1</sup>

#### For colouration:

1 x Bona Craft Oil 2K <sup>2</sup>

2 x Bona Traffic HD

Cleaning and superficial abrasion

1 – 2 x Bona Traffic HD

**Observe:** It is **not** recommended to apply more than two full coats of primer and/or lacquer per day due to risk of excessive wood swelling. Ensure good ventilation during drying. Poor drying conditions may reduce product performance and adhesion.

### **APPLICATION**

- 1) Shake the lacquer container thoroughly and add the hardener component. Immediately proceed to shake the mixture carefully for one minute. Use the mixture directly or at least within four hours. If mixing smaller quantities of lacquer, then one section on the hardener bottle corresponds to 1 litre of lacquer.
- 2) Apply using a Bona Roller at 8 10 m²/ L. Roll alternately across and with the grain of the wood avoiding accumulations of product. Always maintain a "wet edge" to avoid overlaps.
- 3) Allow to dry properly before applying further layers. Ensure proper ventilation.
- 4) If necessary, make an intermediate sanding using the Bona Scrad System P150 grit (or finer) and remove dust before applying a final layer of lacquer. **Note:** If the previous layer of lacquer / primer has been allowed more than 24 hours drying time then an intermediate sanding is always required.

The floor will take light foot traffic approximately 6 hours after the final application and may be put into full use after 12 hours.

Allow the surface to dry for at least three days before covering with carpets or other floor coverings. Avoid placing heavy objects or damp mopping the floor during this time. **Note:** If Bona Traffic HD has been combined with Bona Craft Oil 2K then the surface must be allowed to cure for one week before the surface is covered.

### **RECOATING**

Detailed recoating instructions are available on the Bona Traffic HD product page at www.bona.com.au



Previously lacquered surfaces:

<sup>&</sup>lt;sup>1</sup> the surface should receive three coats in total.

<sup>&</sup>lt;sup>2</sup> to minimise the potential for oil bleed back, it is advised to control and restrict the application rate. Using a cloth wrapped around a pad under a buffing machine for application helps maintain the oil at the surface.



TWO COMPONENT, WATERBORNE COATING

## Powerful performance at top speed

### **MAINTENANCE**

Cleaning with the correct products is easy; When you choose Bona cleaning and maintenance products you can relax knowing that you have chosen the best possible product to help you care for your floor.

End user maintenance instructions are available at bona.com.au. Detailed maintenance instructions are available for both homeowners and professional end users. **Please print out a copy of the relevant instructions and give it to the end user**.

### **IMPORTANT!**

- Plasticisers found in materials such as carpet underlays, furniture legs, castors and adhesives used for fixing can lead to softening and discolouration. Exposure to hair dyes or rubber tyres on cycles, baby strollers, etc. can lead to permanent discolouration of the surface. Use protection or completely avoid contact.
- Spills should be removed promptly. Unattended spills may cause cosmetic stains or damage the surface.
  Please note that whilst Bona lacquers are designed to provide a sealed surface that is resistant to wear,
  scuffing and spillage, etc. no surface applied finish system can prevent physical damage to the timber or
  "harden" the floor. Indentations in the wood and scratches may be caused by furniture, dropped items, dog
  claws, etc. and steps should be taken to reduce the possibility of this occurring.

The information in this document and all other advice and recommendations that we provide to help and assist the applicator are based on previous experience and extensive testing but makes no claim to be complete. Because of the wide range of possible uses and conditions of application of our products, we do not relieve users from the need to carry out their own trials or to seek technical advice from Bona before use. Bona can only guarantee its products and not the construction as a whole. Observe recommendations from flooring manufacturer and the provisions of relevant standards.

