



Bona Wave 2K

TWO COMPONENT, WATERBORNE COATING



Waterborne 2-component lacquer for the surface treatment of wood floors in both commercial and domestic areas with light to moderate traffic intensity. Easy to use, it brings a light surface appearance, together with a low solvent content.

TECHNICAL DATA

Type of lacquer:	2-component waterborne polyurethane topcoat
Sheen (at 60°):	Silk matt 50%, Matt 20%
Mixing ratio:	1 part Wave Hardener to 1 litre Wave 2K (4 vol.%) 0,2 L hardener to 4,8 L lacquer
Pot life:	4 hours at 20° C (shorter if warmer)
Dilution:	If required, dilute with 4% Bona Retarder for a longer open time.
Drying time, until:	- Ready for sanding/recoating: 2 - 3 hours* - Light use: 24 hours* - Full hardness: 7 days* *Under normal climate conditions, 20° C / 60% R.H.
Application tools:	Bona Roller or Bona Swivel Head Bar Applicator
Application rate:	8 - 10 m ² / L per coat
Safety	Lacquer: Unclassified Hardener: Classified. (see Safety Data Sheet).
Cleaning:	Wipe tools free from residual material before cleaning with a minimum of water. Dried material can be removed with acetone.
Shelf life:	Finish - 1 year from date of production in unopened original container Hardener - 18 months from date of production in unopened original container)
Storage/transport:	The temperature must not fall below +5° C or exceed +30° C during storage and transport.
Disposal:	Wastes and emptied containers should be handled in accordance with local regulations.
Pack size:	5 litres incl. hardener
Certificates:	EMICODE EC1 Very low emission

2025-03-25

This data sheet replaces all previous versions
please check bona.com.au to ensure you have the latest version.



Bona Wave 2K

TWO COMPONENT, WATERBORNE COATING

Additional detailed information is noted in the appropriate Safety Data Sheet.

PREPARATION

Ensure the floor is acclimatised to its end-use environment, well sanded, dry, and free from sanding dust, oil, wax and other contamination.

Allow the lacquer and hardener to reach room temperature, insert filter and shake the container thoroughly before use. Optimal conditions for use are between 18 - 25° C and 30 - 60% relative humidity. High temperatures and low humidity shorten drying times, low temperatures and high humidity lengthen drying times.

Minimum temperature for use is 13° C.

TREATMENT SCHEDULE

1 x Bona Primer

1 x Bona Wave 2K

Light sanding 150 grit

1 x Bona Wave 2K

Observe: It is not recommended to apply more than two full coats of primer and/or lacquer per day due to risk of excessive wood swelling. Ensure good ventilation during drying. Poor drying conditions may reduce product performance and adhesion.

APPLICATION

- 1) Shake the lacquer container thoroughly and add the hardener component. Immediately shake the mixture carefully for one minute.
Use the mixture directly or at least within four hours. If mixing smaller quantities of lacquer, then one section on the hardener bottle corresponds to one litre of lacquer.
- 2) Apply using a Bona Roller or Swivel Head Applicator at 8 – 10 m² / L. Roll alternately across and with the grain of the wood avoiding accumulations of product. Always maintain a “wet edge” to avoid overlaps.
- 3) Allow to dry properly before applying further layers. Ensure proper ventilation.
- 4) If necessary, make an intermediate sanding using the Bona Scrad System P150 grit (or finer) and remove dust before applying a final layer of lacquer. Note: If the previous layer of lacquer/primer has been allowed more than 24 hours drying time then an intermediate sanding is always required.

Light foot traffic can be resumed after eight hours but the surface remains susceptible to scratching and marring until fully cured. Full cure is achieved after approximately seven days. Do not cover or damp-mop the surface until fully cured.



Bona Wave 2K

TWO COMPONENT, WATERBORNE COATING

MAINTENANCE

Cleaning with the correct products is easy; When you choose Bona cleaning and maintenance products you can relax knowing that you have chosen the best possible product to help you care for your floor.

End user maintenance instructions are available at bona.com.au. Detailed maintenance instructions are available for both consumers and commercial end users. **Please print out a copy of the relevant instructions and give it to the end user.**

IMPORTANT!

- Plasticisers found in materials such as carpet underlays, furniture legs, castors and adhesives can lead to softening and discolouration. Exposure to hair dyes or rubber tyres on cycles, baby strollers, etc. can lead to permanent, irreversible discolouration of the surface. Use protection or completely avoid contact.
- Spills should be removed promptly. Unattended spills may cause cosmetic stains or damage the surface. Please note that whilst Bona lacquers are designed to provide a sealed surface that is resistant to wear, scuffing and spillage, etc. no surface applied finish system can prevent physical damage to the timber or “harden” the floor. Indentations in the wood and scratches may be caused by furniture, dropped items, dog claws, etc. and steps should be taken to reduce the possibility of this occurring.

The information in this document and all other advice and recommendations that we provide to help and assist the applicator are based on previous experience and extensive testing but makes no claim to be complete. Because of the wide range of possible uses and conditions of application of our products, we do not relieve users from the need to carry out their own trials or to seek technical advice from Bona before use. Bona can only guarantee its products and not the construction as a whole. Observe recommendations from flooring manufacturer and the provisions of relevant standards.