



# Bona DriFast<sup>®</sup> Sealer

An Easy Way to Prime Timber Floors

**Bona<sup>®</sup>**

# Bona DriFast® Sealer

An oil-modified sealer with excellent penetration for bare timber, ease of use and rapid drying time.

Bona DriFast Sealer is a quick drying polyurethane timber floor sealer. It is designed to penetrate and seal bare timber, and is compatible with all Bona water-based top coat finishes.

## Key Benefits

- Easy application
- Penetrates and seals bare timber
- Fast drying time 1.5 - 2 hours
- Rapid hardness development
- Sands easily
- Easy clean up
- Compatible with all Bona water-based top coats

## Technical Data

Type of finish	Oil modified polyurethane primer
Solids content	Approx. 37%
Drying time	1.5 – 2 hours (20°C / 60% RH)
Application tools	Brush, 5mm roller
Coverage rate	15 – 17m <sup>2</sup> per litre
Safety	Classified – see Safety Data Sheet
Clean up	White spirits
Shelf life	2 years in unopened container
Storage	5 – 25°C

## Preparation

Sand and prepare the floor using accepted methods and finish to approximately 120 grit. Stir Bona DriFast Sealer thoroughly before use. Optimal application conditions are 18 – 25°C and 40 – 60% RH. Higher temperatures and lower humidity will shorten drying times. Lower temperatures and higher humidity will lengthen drying times. Minimum temperature for use is 13°C.

## Application

Apply Bona DriFast Sealer using a brush or 5mm roller. A uniform timber saturation and maintenance of a 'wet edge' will avoid colour variation.

When dry, DriFast Sealer **MUST** be abraded thoroughly and evenly using a Bona Scrad pad or a worn 220 grit screen. Move lightly across floor to avoid sanding through the sealer film. Remove all sanding dust and apply 2 coats of Bona water-based top coat.



Available in 3.8 Ltr can

### Additional Information

*Very dense timber species such as Ironbark may be difficult to coat using Bona DriFast Sealer as penetration into the timber is minimal in the heartwood sections. A Bona water-based primer is a good alternative.*

*Natural oils found in and around knots in Cypress Pine may interfere with the drying process.*

*Bona DriFast Sealer should not be used as a final treatment for timber floors and should always be abraded prior to over-coating with a Bona water-based finish.*

*As DriFast Sealer contains drying oils, any cloths or rags should be placed in water or a sealed metal container due to the risk of self-ignition.*

**Bona**®

Bona AB Malmö Sweden

Distributed in Australia by



Adelaide | Brisbane | Melbourne | Perth | Sydney